

Glasstäbe Kalknatronglas

Transparentes Glas

Transformationstemperatur 525°C

Standardlänge ca. 1.500 mm

Außendurchmesser

Ø in mm



Toleranz

Ø aussen in mm

3,00	± 0,10
4,00	± 0,15
5,00	± 0,15
6,00	± 0,15
7,00	± 0,20
8,00	± 0,20
9,00	± 0,20
10,00	± 0,25
12,00	± 0,25
14,00	± 0,30
16,00	± 0,35
20,00	± 0,50
25,00	± 0,70

